



US005881796A

United States Patent [19]
Brown et al.

[11] **Patent Number:** **5,881,796**
[45] **Date of Patent:** ***Mar. 16, 1999**

[54] **APPARATUS AND METHOD FOR
INTEGRATED SEMI-SOLID MATERIAL
PRODUCTION AND CASTING**

[75] Inventors: **Stuart B. Brown**, Needham; **Patricio F. Mendez**, Cambridge; **Christopher S. Rice**, Cambridge; **Shinya Myojin**, Cambridge, all of Mass.

[73] Assignee: **Semi-Solid Technologies Inc.**,
Cambridge, Mass.

[*] Notice: This patent issued on a continued prosecution application filed under 37 CFR 1.53(d), and is subject to the twenty year patent term provisions of 35 U.S.C. 154(a)(2).

[21] Appl. No.: **733,125**

[22] Filed: **Oct. 17, 1996**

[51] Int. Cl.⁶ **B22D 1/00**; B22D 17/08

[52] U.S. Cl. **164/113**; 164/71.1; 164/900

[58] Field of Search 164/900, 71.1,
164/113, 312, 335, 337; 75/10.65, 10.67,
10.14; 148/549

[56] **References Cited**

U.S. PATENT DOCUMENTS

2,745,153 5/1956 Burkett .
3,157,923 11/1964 Hodler .
3,222,776 12/1965 Kawecki 29/ 503

(List continued on next page.)

FOREIGN PATENT DOCUMENTS

0 476 843 A1 3/1992 European Pat. Off. .
0 657 235 A1 6/1995 European Pat. Off. .
0 719 606 A1 7/1996 European Pat. Off. .
0 761 344 A2 3/1997 European Pat. Off. .
0 765 945 A1 4/1997 European Pat. Off. .
2320761 11/1974 Germany 164/312
62-50065 3/1987 Japan .
63-199016 8/1988 Japan .

1-313141 12/1989 Japan 164/900
1-313164 12/1989 Japan .
732073 5/1980 U.S.S.R. 164/335
WO 87/06624 11/1987 WIPO .
WO 95/34393 12/1995 WIPO .
WO 97/12709 4/1997 WIPO .

OTHER PUBLICATIONS

Thesis: "The Machine Casting of High Temperature Semi-Solid Materials", By Danial G. Backman, Massachusetts Institute of Technology, Sep., 1975.

"A World Wide Assessment of Rapid Prototyping Technologies," RF Aubin United Technologies Research Center Report No. 94-13, dated Jan. 1994, 29 pages.

H. L. Marcus and D. L. Bourell, "Solid Freeform Fabrication," *Advanced Materials & Processes*, dated Sep. 1993, pp. 28-31 and 34-35.

S. B. Brown and M. C. Flemings, "Net-Shape Forming Via Semi-Solid Processing," *Advanced Materials & Processes*, dated Jan. 1993, pp. 36-40.

J. W. Comb and W. R. Priedeman, Stratasys, Inc., "Control Parameters and Material Selection Criteria for Rapid Prototyping Systems," copyright date 1993, pp. 86-93.

(List continued on next page.)


Primary Examiner—Kuang Y. Lin

Attorney, Agent, or Firm—Choate, Hall & Stewart

[57] **ABSTRACT**

An apparatus and process is provided for producing semi-solid material and directly casting the semi-solid material into a component wherein the semi-solid material is formed from a molten material and the molten material is introduced into a container. Semi-solid is produced therefrom by agitating, shearing, and thermally controlling the molten material. The semi-solid material is maintained in a substantially isothermal state within the container by appropriate thermal control and thorough three-dimensional mixing. Extending from the container is a means for removing the semi-solid material from the container, including a temperature control mechanism to control the temperature of the semi-solid material within the removing means.

21 Claims, 6 Drawing Sheets



U.S. PATENT DOCUMENTS

3,528,478	9/1970	Koch et al. .	
3,902,544	9/1975	Flemings et al. .	
3,907,192	9/1975	Grietens	228/256
3,920,223	11/1975	Krueger .	
3,932,980	1/1976	Mizutani et al. .	
3,936,298	2/1976	Mehrabian et al. .	
3,948,650	4/1976	Flemings et al. .	
3,951,651	4/1976	Mehrabian et al. .	
3,955,802	5/1976	de Bruyne .	
3,979,026	9/1976	Lee .	
3,993,290	11/1976	Kovich .	
4,008,883	2/1977	Zubietta .	
4,049,204	9/1977	McKee .	
4,065,105	12/1977	Lussiez et al. .	
4,072,543	2/1978	Coldren et al. .	
4,089,680	5/1978	Flemings et al. .	
4,108,643	8/1978	Flemings et al. .	
4,116,423	9/1978	Bennett .	
4,124,307	11/1978	Anisic .	
4,194,552	3/1980	Bennett .	
4,215,628	8/1980	Dodd, Jr. .	
4,229,210	10/1980	Winter et al. .	
4,231,664	11/1980	Flock et al. .	
4,278,355	7/1981	Forberg .	
4,305,673	12/1981	Herbst .	
4,310,124	1/1982	Schwing et al. .	
4,310,352	1/1982	Manfre et al. .	
4,345,637	8/1982	Flemings et al. .	
4,347,889	9/1982	Komatsu et al. .	
4,361,404	11/1982	Colin et al. .	
4,373,950	2/1983	Shingu et al.	75/68 R
4,382,685	5/1983	Pearson .	
4,390,285	6/1983	Durr et al. .	
4,397,687	8/1983	Bye .	
4,434,837	3/1984	Winter et al. .	
4,436,429	3/1984	Strong et al. .	
4,453,829	6/1984	Althouse, III .	
4,469,444	9/1984	Gmeiner et al. .	
4,482,012	11/1984	Young et al. .	
4,506,982	3/1985	Smithers et al. .	
4,534,657	8/1985	Clement .	
4,565,241	1/1986	Young .	
4,565,242	1/1986	Young .	
4,580,616	4/1986	Watts .	
4,620,795	11/1986	Diebold et al. .	
4,635,706	1/1987	Behrens	164/500
4,687,042	8/1987	Young .	
4,694,881	9/1987	Busk .	
4,694,882	9/1987	Busk .	
4,709,746	12/1987	Young et al. .	
4,771,818	9/1988	Kenney .	
4,775,239	10/1988	Martinek et al. .	
4,799,801	1/1989	Bruning .	
4,799,862	1/1989	Davidson et al. .	
4,804,034	2/1989	Leatham et al. .	
4,865,808	9/1989	Ichikawa et al.	428/548
4,874,471	10/1989	Wilmotte .	
4,893,941	1/1990	Wayte .	
4,926,924	5/1990	Brooks et al.	164/5
4,958,678	9/1990	Kawamura et al.	164/461
4,964,455	10/1990	Meyer .	
5,009,844	4/1991	Laxmanan .	
5,037,209	8/1991	Wyss .	
5,085,512	2/1992	Doman .	
5,110,547	5/1992	Kuichi et al. .	
5,121,329	6/1992	Crump	364/468
5,135,564	8/1992	Fujikawa et al. .	
5,144,998	9/1992	Harai et al. .	
5,161,601	11/1992	Abis et al. .	
5,161,888	11/1992	Hauck .	
5,178,204	1/1993	Kelly et al. .	
5,186,236	2/1993	Gabathuler et al. .	
5,219,018	6/1993	Meyer .	
5,257,657	11/1993	Gore	164/46
5,287,719	2/1994	Moritaka et al. .	
5,313,815	5/1994	Nichting et al. .	
5,342,124	8/1994	Swisher, Jr. .	
5,343,926	9/1994	Cheskis et al.	164/46
5,375,645	12/1994	Brueker et al. .	
5,381,847	1/1995	Ashok et al. .	
5,411,330	5/1995	Arutyunov et al. .	
5,464,053	11/1995	Moschini .	
5,478,148	12/1995	Thomas et al. .	

OTHER PUBLICATIONS

Stratasys, Inc., "Rapid Prototyping Using FDM: A Fast, Precise, Safe Technology," paper from the Solid Freeform Fabrication Symposium, Aug. 3-5, 1992, pp. 301-308.

R. E. Reed-Hill and R. Abbaschian, *Physical Metallurgy Principles*, PWS-Kent Publishing Company, 1992, pp. 325-349.

M. E. Orme, K. Willis and J. Courter, Department of Mechanical and Aerospace Engineering, University of California—Irvine, "The Development of Rapid Prototyping of Metallic Components Via Ultra-Uniform Droplet Deposition," undated, pp. 27-36.

J. W. Comb, W. R. Priedeman and P. W. Turley, Stratasys, Inc., "Control Parameters and Material Selection Criteria for Fused Deposition Modeling," undated, pp. 163-170.

M. C. Flemings and K. P. Young, 9th SDCE International Die Casting Exposition and Congress, Jun. 6-9, 1977, "Thixocasting of Steel," Paper No. G-T77-092, dated Jun. 6-9, 1977, 8 pages.

"Structure and Properties of ThioCast Steels" by K.P. Young, et al., *Metals Technology*, Apr. 1979.




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG.5




FIG. 6

APPARATUS AND METHOD FOR INTEGRATED SEMI-SOLID MATERIAL PRODUCTION AND CASTING

This application claims the benefit of copending provisional application "Apparatus and Method for Integrated Semi-Solid Material Production and Casting" filed Oct. 4, 1996 (Express Mail Number EH408038515US, Ser. No. 06/027,595). A related application titled "Apparatus and Method for Semi-Solid Material Production" was filed Oct. 4, 1996 (Express Mail Number EH408038921, Ser. No. 08/726,099) and is incorporated herein by reference.

TECHNICAL FIELD

The present invention relates generally to producing and delivering a semi-solid material slurry for use in material forming processes. In particular, the invention relates to an apparatus for producing a substantially non-dendritic semi-solid material slurry and providing the semi-solid directly to a die casting apparatus.

BACKGROUND INFORMATION

Slurry casting or rheocasting is a procedure in which molten material is subjected to vigorous agitation as it undergoes solidification. During normal (i.e. non-rheocasting) solidification processes, dendritic structures form within the material that is solidifying. In geometric terms, a dendritic structure is a solidified particle shaped like an elongated stem having transverse branches. Vigorous agitation of materials, especially metals, during solidification eliminates at least some dendritic structures. Such agitation shears the tips of the solidifying dendritic structures, thereby reducing dendrite formation. The resulting material slurry is a solid-liquid composition, composed of solid, relatively fine, non-dendritic particles in a liquid matrix (hereinafter referred to as a semi-solid material).

At the molding stage, it is well known that components made from semi-solid material possess great advantages over conventional molten metal formation processes. These benefits derive, in large part, from the lowered thermal requirements for semi-solid material manipulation. A material in a semi-solid state is at a lower temperature than the same material in a liquid state. Additionally, the heat content of material in the semi-solid form is much lower. Thus, less energy is required, less heat needs to be removed, and casting equipment or molds used to form components from semi-solids have a longer life. Furthermore and perhaps most importantly, the casting equipment can process more material in a given amount of time because the cooling cycle is reduced. Other benefits from the use of semi-solid materials include more uniform cooling, a more homogeneous composition, and fewer voids and porosities in the resultant component.

The prior art contains many methods and apparatuses used in the formation of semi-solid materials. For example, there are two basic methods of effectuating vigorous agitation. One method is mechanical stirring. This method is exemplified by U.S. Pat. No. 3,951,651 to Mehrabian et al. which discloses rotating blades within a rotating crucible. The second method of agitation is accomplished with electromagnetic stirring. An example of this method is disclosed in U.S. Pat. No. 4,229,210 to Winter et al., which is incorporated herein by reference. Winter et al. disclose using either AC induction or pulsed DC magnetic fields to produce indirect stirring of the semi-solid.

Once the semi-solid material is formed, however, virtually all prior art methods then include a solidifying and

reheating step. This so-called double processing entails solidifying the semi-solid material into a billet. One of many examples of double processing is disclosed in U.S. Pat. No. 4,771,818 to Kenney. The resulting solid billet from double processing is easily stored or transported for further processing. After solidification, the billet must be reheated for the material to regain the semi-solid properties and advantages discussed above. The reheated billet is then subjected to manipulation such as die casting or molding to form a component. In addition to modifying the material properties of the semi-solid, double processing requires additional cooling and reheating steps. For reasons of efficiency and material handling costs, it would be quite desirable to eliminate the solidifying and reheating step that double processing demands.

U.S. Pat. No. 3,902,544 to Flemings et al., incorporated herein by reference, discloses a semi-solid forming process integrated with a casting process. This process does not include a double processing, solidification step. There are, however, numerous difficulties with the disclosed process in Flemings et al. First and most significantly, Flemings et al. require multiple zones including a molten zone and an agitation zone which are integrally connected and require extremely precise temperature control. Additionally, in order to produce the semi-solid material, there is material flow through the integrally connected zones. Semi-solid material is produced through a combination of material flow and temperature gradient in the agitation zone. Thus, calibrating the required temperature gradient with the (possibly variably) flowing material is exceedingly difficult. Second, the Flemings et al. process discloses a single agitation means. Thorough and complete agitation is necessary to maximize the semi-solid characteristics described above. Third, the Flemings et al. process is lacking an effective transfer means and flow regulation from the agitation zone to a casting apparatus. Additional difficulties with the Flemings process, and improvements thereupon, will be apparent from the detailed description below.

A primary object of the present invention is to provide an apparatus and a process for integrating the formation of semi-solid material with the casting of the semi-solid material while avoiding a solidification and reheating step.

An additional object of the present invention is to provide a more efficient and cost-effective die casting process for use with semi-solid material formation.

Another object of the present invention is to provide semi-solid material formation suitable for casting directly into a component.

Still another object of the present invention is to provide a semi-solid material formation with improved agitation.

Yet another object of the present invention is to provide a semi-solid material formation apparatus integrated with a casting device for casting semi-solid material directly into a component.

SUMMARY OF THE INVENTION

The present invention provides a method and apparatus for producing a component directly from a semi-solid material comprising a source of molten material, a container for receiving the molten material, thermal control means mounted to the container for controlling the temperature of container, an agitation means for agitating the material, and a casting device directly connected to the container. The agitation means and the thermal controlling means act in conjunction to produce a substantially isothermal semi-solid material in the container. A thermally insulated means for

removing the semi-solid material from the container directly provides semi-solid material to the casting device which casts the semi-solid material into a component.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a schematic, front sectional view of a semi-solid production apparatus according to the present invention.

FIG. 2 is a schematic, side sectional view of the apparatus of FIG. 1.

FIG. 3 is a side sectional view of a removal means according to the present invention.

FIG. 4 is a schematic, sectional view of the apparatus of FIG. 1 integrated with a semi-solid casting apparatus according to the present invention.

FIG. 5 is a schematic, side sectional view of the apparatus of FIG. 1 showing an alternate embodiment of the present invention.

FIG. 6 is a schematic, side sectional view of the apparatus of FIG. 1 showing an alternate embodiment of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENT

In FIG. 1, a semi-solid production apparatus is shown generally as reference numeral 10. Separated from the apparatus 10 is a source of molten material 11. Generally any material which may be processed into a semi-solid material 50 is suitable for use with this apparatus 10. The molten material 11 may be a pure metal such as aluminum or magnesium, a metal alloy such as steel or aluminum alloy A356, or a metal-ceramic particle mixture such as aluminum and silicon carbide.

The apparatus 10 includes a cylindrical chamber 12, a primary rotor 14, a secondary rotor 16, and a chamber cover 18. The chamber 12 has an inner bottom wall 20 and a cylindrical inner side wall 22 which are both preferably made of a refractory material. The chamber 12 has an outer support layer 24 preferably made of steel. The top of the chamber 12 is covered by a chamber cover 18. The chamber cover 18 similarly has an insulated refractory layer.

Thermal control system 30 comprises heating segments 32 and cooling segments 34. The heating and cooling segments 32, 34 are mounted to, or embedded within, the outer layer 24 of the chamber 12. The heating and cooling segments 32, 34 may be oriented in many different ways, but as shown, the heating and cooling segments 32, 34 are interspersed around the circumference of the chamber 12. Heating and cooling segments 32, 34 are also mounted to the chamber cover 18. Individual heating and cooling segments 32, 34 may independently add and/or remove heat, thus enhancing the controllability of the temperature of the contents of the chamber 12.

The primary rotor 14 has a rotor end 42 and a shaft 44 which extends upwards from the rotor end 42. The primary rotor shaft 44 extends through the chamber lid 18. The rotor end 42 is immersed in and entirely surrounded by the chamber 12. As shown in FIG. 1, the rotor end 42 has L-shaped blades 43, preferably two such blades spaced 180 degrees apart, extending from the bottom of the rotor end 42. The L-shaped blades 43 have two portions, one of which is parallel to the inner side wall 22 and the other being parallel to the inner bottom wall 20. The L-shaped blades 43, when rotated, shear dendrites which tend to form on the inner side wall 22 and bottom wall 20 of the chamber 12. Additionally, the rotation of the blades 43 promotes material mixing

within horizontal planes. Other blade 43 geometries (e.g. T-shaped) should be effective so long as the gap between the chamber inner side wall 22 and the blades 43 is small. It is desirable that this gap be less than two inches. Furthermore, to promote additional shearing, the gap between the chamber bottom 20 and the blades 43 also should be less than two inches. A typical rotation speed of the shear rotor 14 is approximately 30 rpm.

The secondary rotor 16 has a rotor end 48 and a shaft 46 extending from the rotor end 48. The shape of the rotor end 48 should be designed to encourage vertical mixing of the semi-solid material 50 and enhance the shearing of the semisolid material 50. The rotor end 48 is preferably auger-shaped or screw-shaped, but many other shapes, such as blades tilted relative to horizontal plane, will perform similarly. The shaft 46 extends upwardly from the auger shaped rotor end 48. Depending on the rotational direction of the secondary rotor 16, material in chamber 12 is forced to move in either an upwards or downwards direction. A typical rotation speed of the secondary rotor 16 is 300 rpm.

The primary rotor 14 and the secondary rotor 16 are oriented relative to the chamber 12 and to each other so as to enhance both the shearing and three dimensional agitation of a semi-solid material 50. In FIG. 1 it is seen that the primary rotor 14 revolves around the secondary rotor 16. The secondary rotor 16 rotates within the predominantly horizontal mixing action of the primary rotor 14. This configuration promotes thorough, three-dimensional mixing of the semi-solid material 50.

Although FIG. 1 depicts a plurality of rotors, a single rotor that provides the appropriate shearing and mixing properties may be utilized. Such a single rotor must afford both shearing and mixing, the mixing being three-dimensional so that the semi-solid material 50 in the container 12 is maintainable at a substantially uniform temperature.

The semi-solid material environment into which the rotors 14, 16 are immersed is quite harsh. The rotors 14, 16 are exposed to very high temperature, often corrosive conditions, and considerable physical force. To combat these conditions, the preferred composition of the rotors 14, 16 is a heat and corrosion resistant alloy like stainless steel with a high-temperature MgZrO_3 ceramic coating. Other high-temperature resistant materials, such as a superalloy coated with Al_2O_3 , are also suitable.

A frame 56 is mounted to the chamber lid 18. The frame 56 supports a primary drive motor 58 and a secondary drive motor 60. The respective motors 58, 60 are mechanically coupled to the shafts 44, 46 of the respective rotors 14, 16. As shown in FIG. 1, the primary motor 58 is coupled to the primary rotor shaft 44 by a pair of reduction gears 62 and 64. The primary rotor shaft 44 is supported in the frame 56 by bearing sleeves 66. Similarly, the secondary rotor shaft 46 is supported in frame 56 by bearing sleeve 68. Both motors 58, 60 may be connected to the rotors through reduction or step-up gearing to improve power and/or torque transmission.

An alternative to the mechanical stirring described above is electromagnetic stirring. An example of electromagnetic stirring is found in Winter et al., U.S. Pat. No. 4,229,210. Electromagnetic agitation can effectuate the desired isothermal, three-dimensional shearing and mixing properties desired in the present invention.

Molten material 11 may be delivered to the chamber 12 in a number of different fashions. In one embodiment, the molten material 11 is delivered through an orifice 70 in the chamber cover 18. Alternatively, the molten metal 11 may be

delivered through an orifice in the side wall **22** (not shown) and/or through an orifice in the bottom wall **20**.

Semi-solid material **50** is formed from the molten material **11** upon agitation by the primary rotor **14** and the secondary rotor **16**, and appropriate cooling from the thermal control system **30**. After an initial start-up cycle, the process is semi-continuous whereby as semi-solid material **50** is removed from the chamber **12**, molten material **11** is added. However, the rotors **14**, **16** and the thermal control system **30** maintain the semi-solid **50** in a substantially isothermal state.

In addition to controlling the temperature of the chamber **12** thereby maintaining the semi-solid material **50** in a substantially isothermal state, the thermal control system **30** is also instrumental in starting up and shutting down the apparatus **10**. During start-up, the thermal control system should bring the chamber **12** and its contents up to the appropriate temperature to receive molten material **11**. The chamber **12** may have a large amount of solidified semi-solid material or solidified (previously molten) material remaining in it from a previous operation. The thermal control system **30** should be capable of delivering enough power to re-melt the solidified material. Similarly, when shutting down the apparatus **10**, it may be desirable for the thermal control system **30** to heat up the semi-solid material **50** in order to fully drain the chamber **12**. Another shut-down procedure may entail carefully cooling the semi-solid **50** into the solid state.

As shown in FIG. 2, removal of semi-solid material **50** formed in the chamber **12** is preferably via a removal tube **72**. A detailed view of the removal tube **72** is shown in FIG. 3. The removal tube **72** has a cylindrical inner wall **74** which is in contact with the removed semi-solid material **50**. The inner wall **74** is preferably a refractory material. A support wall **76** is sandwiched between the inner wall **74** and an outer layer **78**. The support wall **76** is made of a material, such as cast iron, capable of supporting the inner wall **74** and semi-solid material **50** contained therein. The outer layer **78** provides insulation of the removal tube **72** and the semi-solid material **50**. The removal tube **72** also protects the semi-solid material **50** from being contaminated by the ambient atmosphere. Without such protection, an oxide would form on the outside of the semi-solid material and intersperse in any components made therefrom. Provided around the removal tube is a heater **80** to maintain the semi-solid material **50** at the desired temperature.

In FIG. 2, the removal port **72** extends from the apparatus **10** through the chamber cover **18**. In an alternative preferred embodiment, the removal port **72** extends from the chamber side wall **22** which has an outlet orifice **112** as shown in FIG. 5. Alternatively, FIG. 5 also shows a removal port **73** extending from the bottom wall **20** which has an outlet orifice **113**. In either case, as described above, the removal port includes a heater **80** to maintain the isothermal state of the semisolid material **50** being removed.

Effectuating semi-solid **50** flow through the port **72** may be achieved by any number of methods. A vacuum could be applied to the removal port **72**, thus sucking the semi-solid out of the chamber **12**. Gravity may be utilized as depicted in FIG. 5 at port **73**. Other transfer methods utilizing mechanical means, such as submerged pistons, helical rotors, or other positive displacement actuators which produce a controlled rate of semi-solid material **50** transfer are also effective.

To further regulate the flow of semi-solid material **50** out of the chamber **12** via any of the removal ports described

above, a valve **83** is provided in the port **72**. The valve **83** can be a simple gate valve or other liquid flow regulation device. It may be desirable to heat the valve **83** so that the semi-solid **50** is maintained at the desired temperature and clogging is prevented.

Flow regulation may also be crudely effectuated by local solidification. Instead of a valve **83**, a heater/cooler (not shown) can locally solidify the semi-solid **50** in port **72** thus stopping the flow. Later, the heater/cooler can reheat the material to resume the flow. This procedure would normally be part of a start-up and shut-down cycle, and is not necessarily part of the isothermal semi-solid material production process described above.

Another manner for transferring semi-solid material **50**, which provides inherent flow control, utilizes a ladle **114** as depicted in FIG. 6. The ladle **114** removes semi-solid material **50** from the chamber **12** while a heater **82** which is mounted to the ladle **114** maintains the temperature of the semi-solid material **50** being removed. A ladle cup **115** of the ladle **114** is attached to a ladle actuator **116**. The cup **115** is rotatable to pour out its contents, and the actuator **116** moves the ladle in the horizontal and vertical directions.

To aid in maintaining proper temperature conditions within the chamber **12**, semi-solid material **50** transfer may occur in successive cycles. During each cycle the above-described flow regulation allows a discrete amount of semi-solid material **50** to be removed. The amount of semi-solid material removed during each cycle should be small relative to the material remaining in the chamber **12**. In this manner, the change in thermal mass within the chamber **12** during removal cycles is small. In a typical cycle, less than ten percent of the semi-solid **50** within chamber **12** is removed.

Turning now to FIG. 4, a die caster **84** is directly attached to the removal tube **72** extending from the apparatus **10**. The die caster **84** includes a ram **86**, a shot sleeve **88**, and a die **90**. The removal tube **72** delivers semi-solid material **50** directly to the shot sleeve **88** through an opening in the shot sleeve **92**. The shot sleeve **88** has two open ends **94**, **96**. The shot sleeve is positioned between, and the open ends **94**, **96** face, the die **90** and the ram **86**. The ram **86**, is connected to a piston **98** which is pneumatically actuated by a pneumatic drive **100**. When actuated, ram **86** forces the semi-solid material **50** into the die **90**. The semi-solid material **50** enters a die chamber **102** through a die chamber inlet **104** within the die **90**. The die **90** includes two halves **106**, **108** which separate to expose a die cast component **110** which is removed upon cooling.

The casting device **84** can be any suitable device for forming a component from the semi-solid material **50**. Suitable casting devices include a mold, a forging die assembly as described in the specification of U.S. Pat. No. 5,287,719, or other commonly known die casting mechanisms.

The die caster **84** is not limited to a vertical configuration relative to the apparatus **10** as shown in FIG. 4. The die caster **84** can be positioned relative to the apparatus **10** in any number of orientations. For example, the die caster **84** can be underneath the apparatus **10** such that gravity aids the transfer of semi-solid material **50** through the transfer tube **72** (not shown). Or instead of a vertical orientation, the die caster **84** may lay horizontally relative to the apparatus **10** (also not shown).

In FIGS. 2 and 4, the removal tube **72** extends from the apparatus **10** through the chamber cover **18**. In an alternative preferred embodiment, the removal tube **72** extends from the chamber side wall **22** which has an outlet port **112** as shown

in FIG. 5. Alternatively, FIG. 5 also shows a removal tube 73 extending from the bottom layer 20 which has an outlet port 113. In either case, as described above, the removal tube 72 connects directly to the die casting device 84.

In another preferred embodiment, the chamber side wall 22 is directly adjacent the die casting device 84 (not shown) eliminating the need for the transfer tube 72. The outlet port 112 directly feeds the shot sleeve 88 with semi-solid material 50. The component 110 is formed as described above.

Although not required, it may be desirable to maintain the entire apparatus 10 in a controlled environment (not shown). Oxides readily form on the outer layers of molten materials and semi-solid materials. Contaminants other than oxides also enter the molten and semi-solid material. In an inert environment, such as one of nitrogen or argon, oxide formation would be reduced or eliminated. The inert environment would also result in fewer contaminants in the semi-solid material. It may be more economical, however, to limit the controlled environment to discrete portions of the apparatus 10 such as the delivery of molten material 11 to the chamber 12. Another discrete and economical portion for environmental control may be the removal port 72 (or the ladle 114). At the removal port 72, the semi-solid material 50 no longer undergoes agitation and the material is soon to be cast into a component. Thus, any oxide skin that forms at this stage will not be dispersed throughout the material by mixing in the container 12. Instead, the oxides will be concentrated on the outer layers of the semi-solid. Therefore, to reduce both oxide formation and to reduce high-concentration oxide pockets, a controlled nitrogen environment (or other suitable and economical environment) would be advantageous at the removal port 72 stage.

The following is an example of the above described process and apparatus after the start-up cycle is complete. Molten aluminum at an approximate temperature of 677 degrees Celsius is poured into the chamber 12 already containing a large quantity of semi-solid material. The primary rotor 14 turns at approximately 30 rpm and stirs and shears the aluminum in a clockwise direction. The secondary rotor 16 rotates at about 300 rpm and forces the aluminum upwards and/or downwards while also shearing the aluminum. The combined effect of the two rotors 14, 16 thoroughly agitates and shears the aluminum in three dimensions. The thermal control system 30 maintains the temperature of the aluminum at approximately 600 degrees Celsius such that dendritic structures are formed. The rotors 14, 16 shear the dendritic structures as they are formed. While the thermal control system maintains the temperature of the semi-solid aluminum at approximately 600 degrees Celsius, the rotors 14, 16 continuously mix the semi-solid aluminum keeping the temperature within the material substantially uniform. The solid particle size produced by this particular process is typically in the range of 50 to 200 microns and the percentage by volume of solids suspended in the semi-solid aluminum is approximately 20 percent.

The semi-solid aluminum is transferred from the chamber 12 to the shot sleeve 88 of the die caster 84 through the transfer tube 72. The removal port heater 80 also maintains the semi-solid aluminum at about 600 degrees Celsius. The ram 86 in the caster 84 is actuated by the pneumatic drive 100 and the semi-solid aluminum is forced into the die 90 and component 110 is formed. When the component 110 and die 90 cool to approximately 400 degrees Celsius, the component is removed.

While there have been described herein what are considered to be preferred embodiments of the present invention,

other modifications of the invention will be apparent to those skilled in the art from the teaching herein. It is therefore desired to be secured in the appended claims all such modifications as fall within the true spirit and scope of the invention. Accordingly, what is desired to be secured by Letters Patent of the United States is the invention as defined and differentiated in the following claims.

We claim:

1. An apparatus for directly producing a component from a semi-solid material comprising:

a source of molten material;

a container for receiving said molten material;

a thermal control means for controlling the temperature of said container;

a mechanical agitating device comprising a primary stirring component and a secondary stirring component for three-dimensionally stirring material within said container and acting in conjunction with said thermal control means to produce a substantially isothermal semi-solid material;

a means for removing a portion of said semi-solid material from said container, said removing means being thermally controlled; and

a casting means directly connected to said removing means for receiving said portion of semi-solid material from said removing means and casting said semi-solid material into a component.

2. The apparatus of claim 1 wherein said primary stirring component includes an arm having a first portion being substantially parallel to a side wall of said container.

3. The apparatus of claim 2 wherein said arm of said primary stirring component includes a second portion being substantially parallel to a bottom wall of said container.

4. The apparatus of claim 2 wherein said secondary stirring component is auger-shaped and promotes mixing of said semi-solid material along an axis of said secondary stirring component.

5. The apparatus of claim 4 wherein said casting means comprises a die casting device.

6. The apparatus of claim 5 wherein said mechanical agitating device is a stainless steel coated with a ceramic.

7. The apparatus of claim 1 wherein said removal means comprises a transfer tube.

8. The apparatus of claim 7 wherein said transfer tube includes an inner insulating layer.

9. The apparatus of claim 8 wherein said transfer tube includes a support tube surrounding said insulating layer and an outer layer surrounding said support tube.

10. The apparatus of claim 9 wherein said transfer tube includes a heating mechanism for maintaining the temperature of said semi-solid material passing through said transfer tube.

11. The apparatus of claim 10 wherein said transfer tube includes a flow control means for regulating a flow of semi-solid material through said transfer tube.

12. The apparatus of claim 11 wherein said transfer flow control means includes a valve that regulates said flow of semi-solid material through said transfer tube such that no more than one tenth of said semi-solid material is removed per a removal cycle.

13. The apparatus of claim 11 wherein said transfer tube extends through a cover in said chamber.

14. The apparatus of claim 11 wherein said transfer tube extends through a side wall in said chamber.

15. The apparatus of claim 1 wherein said casting means includes a die, a ram, and a shot sleeve disposed

therebetween, said shot sleeve for receiving said portion of said semi-solid and said ram for forcing said portion into said die to form said component.

16. An apparatus for directly producing a component from a semi-solid material comprising:

- a container for receiving a molten material;
- a thermal control means for controlling the temperature of material in said container;
- a mechanical agitating device comprising a primary stirring component and a secondary stirring component acting with said container for stirring material in said container and acting in conjunction with said thermal control means for producing said semi-solid material;
- said thermal controller and said agitating means maintaining said semi-solid material in a substantially isothermal state; and
- a die casting means connected to said container for directly casting said semi-solid material into said component prior to complete solidification of said semi-solid material.

17. The apparatus of claim 16 wherein said primary stirring component includes a portion being substantially parallel to a side wall of said container.

18. The apparatus of claim 17 wherein said secondary stirring component is augur-shaped.

19. The apparatus of claim 18 wherein said casting means comprises a die casting device.

20. The apparatus of claim 19 wherein said mechanical agitating device is a stainless steel coated with a ceramic.

21. A method of directly producing a component from partially solidified material semi-solid material comprising:

- receiving a molten material in a container;
- forming said molten material into a semi-solid material with an agitating means that includes a primary stirring component and a secondary stirring component acting with the container and a thermal controlling means;
- maintaining said semi-solid material in a substantially isothermal state with said agitating means and said thermal controlling means;
- transferring a portion of said semi-solid material directly to a casting apparatus; and
- casting said portion of said semi-solid material into said component with said casting apparatus prior to complete solidification of said portion.

* * * * *